



# NORDFLEX

## NT-B 0301 1K NITRO

Version: 120524

### DEFINITION

Semi-glossy nitro synthetic paint with fast drying times. Designed to industrial applications that require short time to be dried. It is suitable for use on wood.

The product must be applied in installations that comply with Directive 1999/13/EC.

- The mixing ratio of the Base/Binder is 20/80 in Weight.

### PHYSICAL CHARACTERISTICS OF THE PAINT










<b>Nature:</b>	Nitro synthetic
<b>Appearance:</b>	Semi-glossy (Gloss: 70-80% at 60°)
<b>Specific weight:</b>	1,0-1,1 kg/l at 20°C
<b>Solid content:</b>	37-45 % Weight
<b>Solids by volume (binder):</b>	28 ± 2 %
<b>Solids by volume (ready to use):</b>	16 ± 2 %
<b>Dry film thickness:</b>	35-45 microns (2 coats)
<b>Theoretical yield:</b>	6-8 m <sup>2</sup> /l

### SUBSTRATE AND PREPARATION

**New substrates:** Apply over vinyl, nitro synthetic, epoxy or polyurethane primers

**Old paints:** Sand and degrease (Orbit P360/P400)

### MIXING RATIO AND APPLICATION METHOD

NT-B 0301: Thinner R0801	 A + C	 S	 mm	 bar		
 <b>Aerographic</b>	100:70-80 volume	20"-23" F/4 20°C	1,2- 1,5	2-3	2	10' 20°C
 <b>Airmix</b>	100:40-45 volume	30" F/4 20°C	<i>Follow the manufacturer recommendations</i>			
 <b>Airless</b>	100:25-30 volume	60" F/4 20°C				

# NORDFLEX






# NORDFLEX

## NT-B 0301

### 1K NITRO

#### DRYING TIMES

			<b>THROUGH DRY</b>
<b>20°C</b>	5'-10'	20'-30'	40'-50'

- *Oven drying is not recommended.*
- *Maximum physical-chemical resistance is obtained after 15 days.*

#### REMARKS

Recommended to be used in ventilated spray booth at 20°C.

#### EQUIPMENT CLEANING

Use a cleaning thinner before the pot life has expired.

#### SAFETY

Следуйте инструкциям на этикетке продукта. Для получения более подробной информации, смотрите паспорта безопасности. Краска соответствует государственным нормативно-правовым требованиям в отношении безопасности и гигиены труда и утилизации отходов.

#### STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

#### SHELF LIFE

In unopened original packaging, one year from manufacturing date.

*For any technical information contact with our Customer Attention Service or our Technical Department.*

*UAB Svydis declines any responsibility due to an incorrect use of the product.*